

ReFill PLA

Same Quality, Different Format!

Description

Introducing our ReFill PLA series - the same premium print quality, now coiled on flangeless cardboard cores! Whether you would like to use a masterspool or an adapter to use with your favourite reuseable spool, now you can do it with confidence!

		Test Method	Typical Value
<i>Physical Properties</i>	Density	-	1.24 g/cm ³
	Tensile Modulus	ASTM D882	3495 MPa
	Tensile Strength at Break	ASTM D882	53 MPa
	Elongation at break	ASTM D882	6%

		Test Method	Typical Value
<i>Thermal Properties</i>	Printing Temperature	-	190 – 22°C
	HDT A	ASTM E2092	55°C

Parameter	Value
Filament diameter [mm]	1,75
Diameter tolerance [mm]	+/- 0,05
Oval tolerance [mm]	+/- 0,02

Disclaimer

The information provided in this datasheet is correct to the best of Filamentive Limited's knowledge and is intended for reference purposes only. The user assumes all responsibility for the use of all information and shall verify quality / properties as required for their specific use case. Filamentive Limited shall not be made liable for any damage, injury or loss induced from the use of materials in any application.